

Purolite® A850

PRODUCT DATA SHEET

Acrylic Gel Strong Base Anion Exchange Resin

Purolite A850 is a gel-type 1 strong base anion exchange resin with an acrylic matrix. The acrylic matrix ensures excellent removal of organic matter from a water supply in conjunction with its reversible removal upon regeneration. This resin is regenerated very efficiently with lower levels of sodium hydroxide than those required for a polystyrene based type 1 resin, and yet it has a comparable ability to remove weaker acids including carbonic acid and silica. Its use in combination with a polystyrene based resin (for instance in a mixed bed positioned after the anion unit) can often result in the removal of a wider spectrum of organic compounds than either type of anion resin alone.

Typical Physical and Chemical Characteristics

Application	Organics ;Tannin Removal and Demineralization - Excellent Resistance to Fouling
Polymer Structure	Gel Polyacrylic crosslinked with divinylbenzene
Appearance	Spherical beads
Functional Group	Quaternary Ammonium
Ionic Form as Shipped	Cl ⁻
Total Capacity (min.)	1.25 eq/l (27.3 Kgr/ft ³) (Cl ⁻ form)
Moisture Retention, Cl ⁻ Form	57 - 62 %
Particle Size Range	300 - 1200 µm
<300 µm (max.)	1 %
Uniformity Coefficient (max.)	1.7
Irreversible Swelling (max.)	10 %
Reversible Swelling, Cl ⁻ → OH ⁻ (max.)	15 %
Specific Gravity	1.09
Shipping Weight (approx.)	680 - 730 g/l (42.5 - 45.6 lb/ft ³)
Temp Limit, OH ⁻ Form	35°C (95°F)



Americas
 T +1 610.668.9090
 F +1 484.384.2751
americas@purolite.com

Europe
 T +44 1443 229334
 F +44 1443 227073
europe@purolite.com

Asia Pacific
 T +86 571 876 31382
 F +86 571 876 31385
asiapacific@purolite.com